



## 

報告編號:TK-20-00865-1 次:1 OF 1

報告日期:109年02月20日

#### 喬城實業有限公司

品 名 稱: 產

導盲釘

品 色: 白鐵色砂面 產 顏

供 應 廠 商: 喬城實業有限公司 送 喬城實業有限公司 驗 廠 商:

期: 109年02月13日 件 日 收

試 期: 109年02月13日~109年02月19日 驗 日

備

註: 1.以上資料由顧客提供(收件及試驗日期除外)

> 2.除非另有說明,此報告結果僅對測試之樣品負責 未經本公司事先書面同意,此報告不可部分複製

3.下述報告內容標示#處由顧客提供

#### 本實驗室依據顧客所提供之試驗需求與樣品進行試驗,結果說明如下:

試驗需求:成份分析

產品規範: CNS 3270(2016) 304 類,CNS 3158(2008)

試驗方法: CNS 10006(1984)

試驗結果: 成份分析

NAME							
#試件名稱	C	Si	S	P	Mn	Ni	Cr
	%	%	%	%	%	%	%
導盲釘	0.08	0.43	0.004	0.029	1.02	7.88	17.96
#規範要求	≦0.09	<b>≤</b> 1.05	≦0.035	≦0.045	≦2.04	7.85~10.65	17.80~20.20

備註: 1.本試驗報告依據 CNS 3270 要求,已加入 CNS 3158 製品許可差。

- 2.本試驗報告之試驗地點同實驗室地址。
- 3.本試驗報告取代 TK-20-00865,原試驗報告作廢,報告修改日期 109年 03月 03日。更正領域別 ---- oOo -----

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-



# 台灣檢驗科技股份有限公司 SGS Taiwan Ltd.

## **SAMPLE CARD**

Laboratory Testing \ ISO Certification \ Inspection No. 9, 14th Rd., Taichung Industrial Park, Taichung 40755, Taiwan, R.O.C. Tel:(04) 23591515 (代表號)

Fax: (04) 23592557

**REPORT NO:** 

PAGE NO 1 TK-20-00865



SGS TK-20-00865



材料暨工程實驗室-台中

## 試驗報告

報告號碼:TK-21-05980 數: 1 OF

報告日期:110年 12月 10日

喬城實業有限公司

稱: 不銹鋼導盲釘 產 品 名

商: 喬城實業有限公司 送 驗 件 期: 110年 11月 25日 收 日

期: 110年 11月 25日~110年 12月 06日 試 驗

註: 1.以上資料由顧客提供(收件及試驗日期除外) 備

> 2.除非另有說明,此報告結果僅對測試之樣品負責 未經本公司事先書面同意,此報告不可部分複製

3.下述報告內容標示#處由顧客提供

本實驗室依據顧客所提供之試驗需求與樣品進行試驗,結果說明如下:

試驗需求:鹽霧試驗

試驗方法: CNS 8886(2002)

試驗結果: 鹽靈試驗

樣品名稱	鹽水噴霧8小時後
不銹鋼導盲釘	測試件表面無腐蝕現象產生

註:

1.下列為鹽水噴霧試驗相關條件:

(1)試驗液使用之鹽 :一級試藥 (2)採取溶液濃度 : 5 w/v % NaCl (3)試驗液使用之水 :純水

(4)噴霧之暴露區溫度 (℃)  $: 35.0\pm2.0$ (5)噴霧量 (ml/h/80cm²) 1.6(Avg.)(6)供給空氣壓力 (kgf/cm²) : 1.0 (Avg.)

(7)洗淨方式 : 試驗前維持客戶送樣時之狀態

:試驗後以15~40℃溫水沖洗刷後擦拭並乾燥


(8)採取溶液pH值 : 6.7 (Avg.) (9)試體支撐方式 : 懸吊 (10)保護方式種類 : 無

(11)測試儀器 : WEISS SC450

2.本試驗報告之試驗地點同實驗室地址。

000

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準。



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com.tw/Terms-and-Conditions">http://www.sgs.com.tw/Terms-and-Conditions</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com.tw/Terms-and-Conditions">http://www.sgs.com.tw/Terms-and-Conditions</a>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.





報告編號:TK-21-06474 次:1 OF 1 報告日期:111年01月03日

#### 喬城實業有限公司

產 品 名 316 不銹鋼導盲釘 供 應 喬城實業有限公司 廠 商: 送 驗 喬城實業有限公司 商: 收 日 期: 110年 12月 22日

試 期: 110年 12月 22日~110年 12月 30日 驗

1.以上資料由顧客提供(收件及試驗日期除外)

2.除非另有說明,此報告結果僅對測試之樣品負責 未經本公司事先書面同意,此報告不可部分複製

3.下述報告內容標示#處由顧客提供

本實驗室依據顧客所提供之試驗需求與樣品進行試驗,結果說明如下: 試驗需求:成份分析

產品規範: CNS 3270(2016) 316 類, CNS 3158(2008)

試驗方法: CNS 10006(1984)


試驗結果:

成份分析

75 17 77 17								
#試件名稱	С	Si	S	P	Mn	Ni	Cr	Mo
	%	%	%	%	%	%	%	%
316 不銹鋼導盲釘	0.03	0.46	0.023	0.025	1.65	10.29	17.15	1.97
#規範要求	<b>≤</b> 0.09	≦1.05	≦0.035	≦0.045	≦2.04	9.85~14.15	15.80~18.20	1.90~3.10

備註: 1.本試驗報告依據 CNS 3270 要求,已加入 CNS 3158 製品許可差。

2.本試驗報告之試驗地點同實驗室地址。



---- 000 -----

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準。

簽

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com.tw/Terms-and-Conditions">http://www.sgs.com.tw/Terms-and-Conditions</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com.tw/Terms-and-Conditions">http://www.sgs.com.tw/Terms-and-Conditions</a>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.



材料暨工程實驗室-台中

## 試驗報告

報告編號:TK-21-06114 頁 次:1 OF 1 報告日期:110年12月10日

#### 喬城實業有限公司

產 品 名 稱: 不銹鋼導盲釘 #316

送 驗 廠 商: 喬城實業有限公司

收 件 期: 110年11月25日 日

試 驗 期: 110年 11月 25日~110年 12月 01日

1.以上資料由顧客提供(收件及試驗日期除外)

2.除非另有說明,此報告結果僅對測試之樣品負責 未經本公司事先書面同意,此報告不可部分複製

3.下述報告內容標示#處由顧客提供

## 本實驗室依據顧客所提供之試驗需求與樣品進行試驗,結果說明如下:

試驗需求:成份分析

試驗方法: CNS 10006(1984)

試驗結果:

成份分析

偌

#試件名稱	C	Si	S	P	Mn	Ni	Cr	Mo
	%	%	%	%	%	%	%	%
不銹鋼導盲釘 #316	0.022	0.41	0.0014	0.022	0.97	9.38	16.95	1.35

備註:本試驗報告之試驗地點同實驗室地址。

---- 000 -----

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準。

報告 簽署

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com.tw/Terms-and-Conditions">http://www.sgs.com.tw/Terms-and-Conditions</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com.tw/Terms-and-Conditions">http://www.sgs.com.tw/Terms-and-Conditions</a> and, for indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or refer only to the sample(s) tested.

f (886-4) 2359-2557



材料暨工程實驗室-台中

## 試驗報告

報告編號:TK-21-06114 頁 次:1 OF 1

報告日期:110年12月10日

#### 喬城實業有限公司

產 品 名 稱: 不銹鋼導盲釘 #316

送 驗 廠 商: 喬城實業有限公司 件 收 日 期: 110年11月25日

試 期: 110年 11月 25日~110年 12月 01日 驗 日

備 1.以上資料由顧客提供(收件及試驗日期除外)

> 2.除非另有說明,此報告結果僅對測試之樣品負責 未經本公司事先書面同意,此報告不可部分複製

3.下述報告內容標示#處由顧客提供

本實驗室依據顧客所提供之試驗需求與樣品進行試驗,結果說明如下:

試驗需求:成份分析

試驗方法: CNS 10006(1984)

試驗結果:

成份分析

#試件名稱	С	Si	S	P	Mn	Ni	Cr	Mo
	%	%	%	%	%	%	%	%
不銹鋼導盲釘 #316	0.022	0.41	0.0014	0.022	0.97	9.38	16.95	1.35

備註:本試驗報告之試驗地點同實驗室地址。

---- 000 -----



本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準。

報告簽署

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com.tw/Terms-and-Conditions">http://www.sgs.com.tw/Terms-and-Conditions</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com.tw/Terms-and-Conditions">http://www.sgs.com.tw/Terms-and-Conditions</a>. Attention is drawn to the limitation of liability, and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report.

f (886-4) 2359-2557



報告編號:TV-21-04043

數: 1 OF 2

報告日期:110年12月09日

#### 喬城實業有限公司

稱: 不銹鋼導盲釘 名

廠 喬城實業有限公司 驗 商: 收 期: 110年 11月 26日 件 日

期: 110年 11月 26日~110年 12月 09日 驗 日

註: 1.以上資料由顧客提供(收件及試驗日期除外)

2.除非另有說明,此報告結果僅對測試之樣品負責 未經本公司事先書面同意,此報告不可部分複製

3.下述報告內容標示#處由顧客提供

## 本實驗室依據顧客所提供之試驗需求與樣品進行試驗,結果說明如下:

試驗需求:

摩擦係數

試驗方法:

摩擦係數-ASTM D1894-14

Static and Kinetic Coefficients of Friction of Plastic Film and Sheeting (C-Type)

試驗結果:

- 請詳附件 -

- - -1- - -

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com.tw/Terms-and-Conditions">http://www.sgs.com.tw/Terms-and-Conditions</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com.tw/Terms-and-Conditions">http://www.sgs.com.tw/Terms-and-Conditions</a>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.



報告編號:TV-21-04043

數: 2 OF 2

報告日期:110年12月09日

#### 試驗設備:

儀器名稱	<b>廠</b> 牌	型號
萬能試驗機	INSTRON	3369

#### 試驗條件:

1.試驗速率: 150±30 mm/min

2.試驗環境: 20±2°C / 65±5%RH

3.摩擦介面:橡膠(Shore Type A 60±5)

4.砝碼+試樣重量:248.35g

5.試驗狀態:乾式

#### 試驗結果:

試驗項目	結果
摩擦係數	1.02 (s=0.031)

註:1.「s」係為標準差

2. 本試驗報告之試驗地點同實驗室地址

#### 試驗照片:



---000---

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com.tw/Terms-and-Conditions">http://www.sgs.com.tw/Terms-and-Conditions</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com.tw/Terms-and-Conditions">http://www.sgs.com.tw/Terms-and-Conditions</a>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.